



TECHNICAL DATA SHEET

Issue: 1-Jul-15

AQUATEX 205

This product is a high wearing, flexible and durable water-based high build texture coating designed specifically for concrete areas requiring extra grip and slip reduction.

FEATURES & BENEFITS

- * Low slip texture finish
- * Hard durable coating
- * Good adhesion
- * Ready for use
- * Clean up with water

PERFORMANCE GUIDE & COMPARISON*

Product	Ease of Application	Preparation	Durability	Maintenance
205	Easy to apply	Medium	High	Low

Characteristic	Typical Value
Colour	Colour Card
Solids (vol. %)	61 - 63%
Gloss	Low
Pack Sizes	20 Kilograms (12 Litres)
Abrasion Resistance	Very good
Chemical Resistance	N/A
Solvent Resistance	N/A

* Performance Guide & Comparison

Description	Evaluation and Meaning
Ease of Application	The level of effort and expenditure to apply the coating, combined with level of expertise. <i>High = very easy to apply; Medium = easy to apply; Low = presents challenges for inexperienced users.</i>
Preparation	The level of effort and expense for preparing the substrate for coating. <i>High = a high level of effort and expertise required for preparation; Medium = modest preparation required; Low = low to no preparation required.</i>
Durability	The expected performance under standard Australian conditions for weathering and temperature variation. <i>High = High level of durability under extreme conditions; Medium = meets or exceeds standard conditions; Low = meets standard conditions, but not expected to endure.</i>
Maintenance	The level of continued coating support, or re-coating to achieve the same level of performance. <i>High = a high level of effort and expenditure in cleaning, or re-coating the system; Medium = a modest level of effort and expenditure for cleaning to keep the coating looking good and performing well; Low = almost no effort to support the coating system after application.</i>



TECHNICAL DATA SHEET

Issue: 1-Jul-15

APPLICATION

Apply by roller, hopper gun, broom or squeegee. Allow to dry between coats.

Spread-rate:

	Minimum	Maximum	Typical
Theoretical Spread Rate (m ² /L)	2.5	5	3.5
Wet Film Thickness (µm)	400	200	300
Dry Film Thickness (µm)	250	120	180

Dry Times**

Substrate Temperature	5 C	10 C	20 C	30 C
Surface Dry (hours)	N/A	6	4	2
Hard Dry (hours)	N/A	24	18	12
Recoat Time (hours)	N/A	24	18	12

** Drying times are generally related to air circulation, temperature, and film thickness. The figures given above are typical with good ventilation, typical film thickness and single coat application.

SURFACE PREPARATION

Surfaces must be clean (free from dirt, grease or other foreign matter) and dry.

DIRECTIONS FOR USE

Thoroughly stir contents and check colour before application. Thin with water to 5% maximum.

SAFETY

Keep away from heat and flame. No smoking. Provide adequate ventilation and wear protective clothing. Consult safety data sheet.

Failure to observe these precautions will void all warranties and guarantees for product performance. The manufacturer will take no responsibility for coatings, products, labour, corrective action, or compensation where there is evidence of failure to abide by the manufacturer's directions.

CLEAN UP

Clean up with water.

DISCLAIMER

Do not apply this product if there is uncertainty about application or surface preparation. This Product Data Sheet is to be used as a guide only; it is NOT a specification.